



# Bituminous Emulsion – Cationic Tack Coat



C40 B7  
According to CYS EN 13808:2005

## Specifications

Property	Test Method	Result
<b>Tests on Emulsion</b>		
Particle Polarity	EN 1430	Class 2, Positive
Breaking Value	EN 13075-1	Class 7, $\geq 220$
Residue on Sieving 500 $\mu\text{m}$ sieve (% by mass)	EN 1429	Class 2, $< 0.1$
Binder Content (by water content), % by mass	EN 1428	Class 2, 38-42
Recovered Binder Content (by distillation)	EN 1431	Class 0, NPD*
Oil Distillate Content	EN1431	Class 0, NPD
Efflux Time @ 40 °C (seconds)	EN 12846	Class 2, $< 20$
Adhesivity - % Coating	EN 13614	Class 0, NPD
<b>Tests on Residue</b>		
Penetration (25 °C, 0.1 mm)	EN 1426	Class 3, $\leq 100$
Softening Point (°C)	EN 1427	Class 4, $\geq 43$

\*NPD: No Performance Determined

A.N.C Waterproofing Industries, Ltd.  
Anatolikon Industrial Area  
P.O. Box 60268  
Paphos 8101 - Cyprus  
Tel: +357 26422860 Fax: +357 26422684  
e-mail: ancwater@cytanet.com.cy